

PRODUCT : 6CRSB999
DESCRIPTION: Hygiene Plus Agent for Solvent Borne Products
USE: Interior Cabinetry, Fixtures and Furniture

CHEMICAL - PHYSICAL CHARACTERISTICS

SPECIFIC GRAVITY: 1.00 ± 0.100 (Kg/l at 20°C)
DENSITY (WPG): 8.35 ± 0.100 (lbs/gal US at 68° F)
WEIGHT SOLIDS: 99% ± 1
VOLUME SOLIDS: 99% ± 1
VOC (material): 0.00 lbs/gal US or 0.00 g/l
VOC (coating): 0.00 lbs/gal US or 0.00 g/l
VOC Ratio: 0.00 lbs VOC/lbs Solids
HAPS Ratio: 0.00 lbs HAPS/lbs solids

PREPARATION OF THE PRODUCT

You may add 1.5% of 6CRSB999 additive to any solvent borne interior and exterior paint of the following technology: 2K urethane technology (PU), 2K acrylic technology, U.V. technology. This additive can't be added to acid catalysed products, neither on the pre-cat not to the post cat or conversion varnish. This product must be added and mixed well before adding the recommended hardener and reducer.

This product meets U.S.A. TSCA regulations.

DSL Inventory: all the components are listed on the DSL inventory.

GENERAL PROPERTIES

6CRSB999 Has been developed to give finished surfaces a bacterial free surface. This additive has been tested according to ISO 22196:2011. This additive must be added to the solvent borne base and mixed well before adding the recommended hardener and reducer. This additive remains active in the base for at least one month if stored in a sealed container. With the use of this additive, the finished surface will remain bacterial free for the entire life of the substrate. High gloss surfaces that have been polished will not loss its antibacterial characteristics.

SHELF LIFE: 1 year

Data refers to product stored in original, sealed packing.

STORAGE: Keep in a cool, well ventilated place; temperature should not exceed 77°- 82.4° F.

Company Information: SIRCA S.p.A. has a quality system certified by DNV GL ISO 9001



The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products.