

PRODUCT : 6CTH46S06
DESCRIPTION: PU Hardener for Special Wet Look Topcoats

CHEMICAL - PHYSICAL CHARACTERISTICS

| | |
|--------------------------|------------------------------------|
| SPECIFIC GRAVITY: | 0.98 ± 0.100 (Kg/l at 20°C) |
| DENSITY (WPG): | 8.18 ± 0.100 (lbs/gal US at 68° F) |
| WEIGHT SOLIDS: | 37% ± 1 |
| VOLUME SOLIDS: | 29.14% ± 1 |
| VOC (material): | 5.15 lbs/gal US or 617.40 g/l |
| VOC (coating): | 5.15 lbs/gal US or 617.40 g/l |
| VOC Ratio: | 1.70 lbs VOC/lbs Solids |
| HAPS Ratio: | 0.354 lbs HAPS/lbs solids |

This product meets U.S.A. TSCA regulations.

GENERAL PROPERTIES

This Polyisocyanate Hardener for PU topcoats shows good elasticity, wetting properties and long pot-life. This hardener has been developed for glossy clear and pigmented PU topcoats. It has excellent light fastness and it is fast drying.

This is the recommended hardener for 6LPU136 and 6LPP2630NC PU Wet Look Topcoats.

For further information, please refer to our technical representatives.

SHELF LIFE: 1 year
Data refers to product stored in original, sealed packing.

STORAGE: Keep in a cool, well ventilated place; temperature should not exceed 77°- 82.4° F.

Company Information: SIRCA S.p.A. has a quality system certified by DNV GL ISO 9001

◇◇◇◇◇◇◇◇◇◇

The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products.