

PRODUCT : 6CR4110
DESCRIPTION: Adhesion promoter for glass

CHEMICAL - PHYSICAL CHARACTERISTICS

SPECIFIC GRAVITY: 1.065 ± 0.100 (Kg/l at 20°C)
DENSITY (WPG): 8.89 ± 0.100 (lbs/gal US at 68° F)
WEIGHT SOLIDS: 99% ± 1
VOLUME SOLIDS: 98.90% ± 1
VOC (material): 0.09 lbs/gal US or 10.65 g/l
VOC (coating): 0.09 lbs/gal US or 10.65 g/l
VOC Ratio: 0.01 lbs VOC/lbs Solids
HAPS Ratio: 0.00 lbs HAPS/lbs solids

This product meets U.S.A. TSCA regulations.

GENERAL PROPERTIES

Adhesion promoter for glass and inorganic substrates.

Adhesion promoter for polyurethane and waterborne paints needs to be mixed under constant agitation (homogeneous stirring). Using this additive can cause the viscosity of your coating to increase which could cause flow and lay issues.

The recommended mixing percentage is up to 4%. It is recommended to add this adhesion promoter to the desired base just before applying the coating to glass. This glass promoter will dissipate over the course of one working day. It is not recommended to add the glass promoter to a base that will not be used during the one day time frame. It is also not recommended to re-add the adhesion promoter to the original left over base.

Do not use the product with temperature below 15°C and when relative humidity is high, since it could have bad influence on the drying times and the stackability properties.

For further information, please refer to our technical representatives.

SHELF LIFE: 1 year
Data refers to product stored in original, sealed packing.

STORAGE: Keep in a cool, well ventilated place; temperature should not exceed 77°- 82.4° F.

Company Information: SIRCA S.p.A. has a quality system certified by DNV GL ISO 9001



The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products.